



Polypropylene FR4850

Halogen Free Flame Retardant Polypropylene Compound

Description

FR4850 is a halogen free flame retardant polypropylene compound for Primary Automotive Wire.

Applications

FR4850 is intended for use as a 125 °C rated primary insulation for automotive thin wall wires of 1.5 mm² or 16 AWG conductors and finer.

Specifications

FR4850 meets the applicable requirements as below when processed using sound extrusion practice and testing procedure:

SAE J1128/J1127
GMW15626
Chrysler MS-12441

Ford ES-AU5T-1A348-AA
ISO 6722

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (Compound) (23 °C)	1350 kg/m ³	ISO 1872-2/ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	0,7 g/10min	ISO 1133
Tensile Strain at Break	> 300 %	IEC 60811-1-1
Tensile Strength	> 20 MPa	IEC 60811-1-1
Retention of Elongation after Ageing (168 h, 165 °C)	> 50 %	SAE J1128
Retention of Tensile Strength after Ageing (168 h, 165 °C)	> 50 %	SAE J1128
Brittleness temperature	< -40 °C	ISO 6722
Hardness, Shore D	70	ISO 868

Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Dielectric constant (50 Hz) ¹	3	IEC 250
¹ 23 °C		

Other properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Limiting Oxygen Index	27 %	ISO 4589-2
Flame Test	Pass	ISO 6722/SAE J1128
UL Horizontal Flame Test	Pass	UL2556



Polypropylene FR4850

Needle Scrape Abrasion
Sandpaper Abrasion
Long term heat ageing (3000 h, 125 °C)

Pass
Pass
Pass

ISO 6722
ISO6722/SAE J1128
ISO 6722

Processing Techniques

A melt temperature of 250 °C and preheating of the conductor is recommended.

Packaging

Package: Smallbins

Package: 25 kg Bags

Storage

FR4850 normally does not need pre-drying unless the material has been stored in a moist environment for a long period. In such cases drying in dehumidified air for 4 hours at 70°C will normally reduce the moisture content to an acceptable value.

Safety

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.



Polypropylene
FR4850

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.